

Armatex® G 65/65

Woven geogrid for soil reinforcement

Technical data sheet

Product description

Polymer	Density	Melting Point	Construction
100% Polyester geogrid with PVC coating	1,38 kg/dm³	250 °C	Multifilament

Properties

Mechanical Properties	Standard	Performance	Tolerance
Tensile strength - MD	EN ISO 10319	75 kN/m	-10 kN/m
Tensile strength - CMD	EN ISO 10319	75 kN/m	-10 kN/m
Elongation at maximum load - MD	EN ISO 10319	12 %	+/-2,5 %
Elongation at maximum load - CMD	EN ISO 10319	12,5 %	+/-2.5 %
Tensile strength at 2% elongation - MD	EN ISO 10319	12 kN/m	
Tensile strength at 2% elongation - CMD	EN ISO 10319	12 kN/m	
Tensile strength at 3% elongation - MD	EN ISO 10319	14 kN/m	
Tensile strength at 3% elongation - CMD	EN ISO 10319	14 kN/m	
Tensile strength at 5% elongation - MD	EN ISO 10319	17 kN/m	
Tensile strength at 5% elongation - CMD	EN ISO 10319	17 kN/m	

Dimensions

Aperture size		20 x 20 / 35 x 35 mm	
Weight	EN ISO 9864	400 g/m²	+/-40 g/m²
Length (+/- 1%) x width (+/- 1%)		100 x 5 m	
Length / diameter of roll		5,05 / 0,38 m	
Gross weight		210 kg	
Truck Load Volume (+/- 10%)		35000 m³	
Color code		Brown	

Version date : 1.7.2013

Durability

Predicted minimal durability in years in natural soils with 4 < pH < 9 and soil temperatures < 25°C	Annex B	25	
Maximum allowed time between installation and covering of the geosynthetic	EN 12224	2 weeks	

Version n° 1

The Quality Management System of Bonar has been approved to the ISO 9001 Quality Management System Standard. Certificates are available on request.



The information set forth in this data sheet reflects the best knowledge at the time of publication. The document is subject to change pursuant to new developments and findings. The same reservation applies to the properties of the products described. No liability is undertaken for results obtained by usage of the products and information.