

Armatex® RSM PP 80/80

Knitted geocomposite for reinforcement of asphalt pavements and soils

Technical data sheet

Product description

Polymer	Density	Melting Point	Construction
PVA geogrid with PP nonwoven	1.27/0.91 kg/dm ³	200/165 °C	Multifilament/nonwoven

Properties

Mechanical Properties	Standard	Performance	Tolerance
Tensile strength - MD	EN ISO 10319	88 kN/m	-8 kN/m
Tensile strength - CMD	EN ISO 10319	88 kN/m	-8 kN/m
Elongation at maximum load - MD	EN ISO 10319	5 %	+/-2 %
Elongation at maximum load - CMD	EN ISO 10319	5 %	+/-2 %
Tensile strength at 2% elongation - MD	EN ISO 10319	32 kN/m	
Tensile strength at 2% elongation - CMD	EN ISO 10319	32 kN/m	
Tensile strength at 3% elongation - MD	EN ISO 10319	48 kN/m	
Tensile strength at 3% elongation - CMD	EN ISO 10319	48 kN/m	
Tensile strength at 5% elongation - MD	EN ISO 10319	64 kN/m	
Tensile strength at 5% elongation - CMD	EN ISO 10319	64 kN/m	

Dimensions

Aperture size		n/a	
Weight	EN ISO 9864	365 g/m ²	35 g/m ²
Length (+/- 1%) x width (+/- 1%)		100 x 5,2 m	
Length / diameter of roll			
Gross weight		200 kg	
Truck Load Volume (+/- 10%)		-	
Color code		Grey	

Version date : 1.7.2013

Durability

Predicted minimal durability in years in natural soils with 4 < pH < 9 and soil temperatures < 25°C	Annex B	25	
Maximum allowed time between installation and covering of the geosynthetic	EN 12224	2 weeks	

Version n° 1

The Quality Management System of Bonar has been approved to the ISO 9001 Quality Management System Standard. Certificates are available on request.



The information set forth in this data sheet reflects the best knowledge at the time of publication. The document is subject to change pursuant to new developments and findings. The same reservation applies to the properties of the products described. No liability is undertaken for results obtained by usage of the products and information.